

TECHNICAL CHARACTERISTICS

wineo 600

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

wineo

	wineo 600 wood	wineo 600 wood XL	wineo 600 stone XL	
Format	1200 x 180 mm	1505 x 235 mm	914 x 457 mm	
Product thickness	2 mm	2 mm	2 mm	
Planks, tiles / m² per box	18 / 3.89 m ²	12 / 4.24 m ²	12 / 5.01 m ²	
Boxes / m² per pallet	60 / 233.40 m ²	64 / 271.36 m ²	52 / 260.52 m ²	
Guarantee Extended warranty	20 years for private use according to Windmüller warranty conditions - www.wineo.de + 5 years for laying on PU underlay mat			

Classification		Product composition	
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage	1 Surface seal
	Utilization class 32 EN ISO 10874	Commercial sector with average usage	2 Surface texture Various embossings
	Utilization class 41 EN ISO 10874	Light industry sector with moderate usage	3 Wear layer Thickness 0.4 mm
	Wear layer binder content EN ISO 10582	Typ I	4 Design Decor film
	R9 Anti slip category DIN 51130	R 9	5 Base layer
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time	6 Backing
	Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6	7 Underlay material silentPLUS (available separately)
	Residual indentation EN ISO 24343-1	≤ 0,1 mm without underlay mat ~ 0.17 mm with silentPREMIUM	
	Castor chair test ISO 4918	25000 revolutions no damage with rolls type W	
	Thermal resistance EN 12667	≤ 0.011 (m ² K)/W without underlay mat ≤ 0.021 (m ² K)/W with silentPREMIUM or silentPLUS	
	Impact sound reduction EN ISO 16251-1	~ 4 dB ~ 17 dB with silentPLUS	
	Dimensional stability EN ISO 23999	~ 0.15 %	
	REACH	free from SVHC substances ≥ 0.1 %	
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203	

CE Windmüller GmbH
Nord-West-Ring 21
D-32832 Augustdorf

DOP: 0301010
EN 14041:2004 / AC2006
1658

- 18 -

E1

DS

HCHO

≤ 2 kV

≥ 0.15 W/(mK)

www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR*

A+ A B C

Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)



Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.